

1998

Chromium Oxides and Lithiated Chromium Oxides. Promising Cathode Materials for Secondary Lithium Batteries

Pankaj Arora

University of South Carolina - Columbia

Dong Zhang

University of South Carolina - Columbia

Branko N. Popov

University of South Carolina - Columbia, popov@engr.sc.edu

Ralph E. White

University of South Carolina - Columbia, white@cec.sc.edu

Follow this and additional works at: https://scholarcommons.sc.edu/eche_facpub

 Part of the [Chemical Engineering Commons](#)

Publication Info

Electrochemical and Solid-State Letters, 1998, pages 249-251.

© The Electrochemical Society, Inc. 1998. All rights reserved. Except as provided under U.S. copyright law, this work may not be reproduced, resold, distributed, or modified without the express permission of The Electrochemical Society (ECS). The archival version of this work was published in *Electrochemical and Solid-State Letters*.

<http://www.electrochem.org/>

Publisher's link: <http://dx.doi.org/10.1149/1.1390702>

DOI: 10.1149/1.1390702

This Article is brought to you by the Chemical Engineering, Department of at Scholar Commons. It has been accepted for inclusion in Faculty Publications by an authorized administrator of Scholar Commons. For more information, please contact digres@mailbox.sc.edu.

Chromium Oxides and Lithiated Chromium Oxides. Promising Cathode Materials for Secondary Lithium Batteries

Pankaj Arora,* Dong Zhang,* Branko N. Popov,** and Ralph E. White**

Center for Electrochemical Engineering, Department of Chemical Engineering, University of South Carolina, Columbia, South Carolina 29208, USA

Chromium oxides and lithiated chromium oxides were synthesized by thermal decomposition of chromium trioxide (CrO_3) at high temperatures and oxygen pressures. Synthesis temperature and pressure markedly affect the performance of these cathode materials. Higher pressures lead to a higher O/Cr ratio and fewer impurities in the final product. These materials are stable intercalation hosts for lithium, and exhibit a higher capacity than any of the prominent positive electrodes used in secondary lithium batteries. $m\text{-CrO}_x$ has a capacity of 255 mAh/g, while $m\text{-LiCrO}_x$ has a capacity of 210 mAh/g, during the first discharge. The average voltage of these cells is 3.0 V vs. Li/Li^+ that gives an average energy density of approximately 650 Wh/Kg.

© 1998 The Electrochemical Society. S1099-0062(98)07-090-4. All rights reserved.

Manuscript submitted July 24, 1998; revised manuscript received August 26, 1998. Available electronically September 29, 1998.

Rechargeable lithium batteries based on chromium oxides as the active cathode material are of considerable interest because of the very high theoretical specific energies of these compounds.¹ Varta developed a primary Li/CrO_x cell which has a specific energy of 270 Wh/kg and with an energy density of 675 Wh/L at low drain rates.² Toyoguchi et al.³ developed a coin-type LiCr_2O_5 secondary battery with an energy density of 170 Wh/L and a cycle life of over 400 cycles. According to Yamamoto and co-workers,^{4,5} the best performance of the chromium oxide cathode was obtained with amorphous Cr_3O_8 cathodes due to the higher surface roughness of the amorphous cathode. Primary Li/AgCrO_4 cells, utilizing organic electrolytes, are manufactured by SAFT.² Bessenhard et al.^{6,7} studied chromium oxides as cathodes for secondary high energy density lithium batteries. According to these studies Cr_2O_5 and Cr_3O_8 have an average discharge voltage of approximately 3.0 V vs. Li/Li^+ and a maximum charge transfer exceeding one electron per Cr atom.

The objectives of this work are to synthesize chromium oxides (CrO_x), lithiated chromium oxides ($m\text{-LiCrO}_x$ and LiCr_3O_8), and to characterize these materials as positive electrodes for secondary lithium batteries.

Experimental

Crystalline CrO_x was obtained by heating CrO_3 (Aldrich, 99.9%) in an autoclave for 24 h at high temperatures under high oxygen pressure. The autoclave was connected with a pressure gauge and temperature controller to monitor and control the pressure and temperature. The synthesis temperatures and pressures used in the preparation of various chromium oxides are reported in Table I. Sample A was prepared at 320°C, while all other samples were prepared at 270°C. The synthesis pressure used was ca. 50 psi for samples A and B, and 400 and 500 psi for samples C and D, respectively. The product was a mixture of CrO_x and residual CrO_3 . The reaction was stopped by quenching the steel cylinder in cold water followed by cooling in a stream of cold air.

Chemically modified CrO_x ($m\text{-CrO}_x$) was prepared by thermal decomposition of CrO_3 in the presence of 2% $(\text{NH}_4)_2\text{SO}_4$ (Aldrich, 99.999%) at 270°C and 500 psi. The CrO_3 impurity was removed by leaching the product five times in distilled water for 1 h. The chemical treatment given to $m\text{-CrO}_x$ modifies the dispersive state of the cathode material and reduces the traces of CrO_3 contamination. Chemically modified $m\text{-CrO}_x$ has different properties than CrO_3 . It is neither hygroscopic nor soluble in water and thus is not a biohazard.

The chemical lithiation of $m\text{-CrO}_x$ was carried out from active LiI dissolved in acetonitrile to produce $m\text{-LiCrO}_x$.⁸ LiCr_3O_8 was prepared by heating a molar ratio mixture of CrO_3 and $\text{Li}_2\text{Cr}_2\text{O}_7$ in a quartz crucible to 350°C for 2 h. The CrO_3 impurity from $m\text{-LiCrO}_x$ and LiCr_3O_8 was removed by leaching the product five times in distilled water for 1

Table I. Synthesis conditions for different chromium oxides prepared in this study.

Sample no.	Temperature (°C)	Pressure (psi)	Chemical treatment
A	320	50	No
B	270	50	No
C	270	400	No
D	270	500	No
$m\text{-CrO}_x$	270	500	Yes

h. The chemical treatment (as described above) helps in increasing the dispersive state and active surface area of $m\text{-LiCrO}_x$.

Electrochemical characterization of the cathode materials was carried out in Swagelok three-electrode cells (T-cell). The anode and reference electrodes were disks of lithium foil, and the separator was a sheet of Whatman glass fiber filter paper. The cathode consisted of a mixture of 87% CrO_x (or $m\text{-LiCrO}_x$), 8.7% carbon black, and 4.3% poly(tetrafluoroethylene) which was pressed into a thin film 50-60 μm thick.

The electrolyte used in this study was 1 M LiPF_6 in a 1:1:3 mixture of propylene carbonate, ethylene carbonate, and dimethyl carbonate (EM Industries). The procedure for the fabrication of electrodes and cells are almost the same as those described previously in detail.^{9,10} Handling of materials and cell assembling was carried out in an Ar-filled glove box (Vacuum Atmospheres, < 5 ppm H_2O).

The X-ray diffraction (XRD) patterns were collected with a Rigaku 405S5 X-ray diffractometer using $\text{Cu K}\alpha$ radiation. The surface area of these oxides was measured using Micrometrics 270 BET (N_2 adsorption).

Cyclic voltammograms for $m\text{-CrO}_x$, $m\text{-LiCrO}_x$, and Li_3CrO_8 were obtained using a scan rate of 0.05 mV/s over a potential range of 2.0-4.3 V vs. Li/Li^+ . The cell performance was evaluated galvanostatically at current density of 0.1 and 0.5 mA/cm^2 at room temperature. The cells were cycled (charge-discharge) on Bitrode (Bitrode Co, MO, USA) cyler within the cutoff potentials.

Results and Discussion

The stoichiometry of the CrO_x samples was determined by a Perkin Elmer TGA7 thermal gravimetric analyzer. The O/Cr ratio was determined by reducing the CrO_x samples to Cr_2O_3 in air at 1°C/min. The decomposition of CrO_x to Cr_2O_3 starts at 385°C. The knowledge of final product stoichiometry (Cr_2O_3) and weight loss (corresponding to O_2 lost or evolved) lead to O/Cr ratio as reported in Fig. 1a. A sample thermal gravimetric analysis (TGA) curve (sample C) and atomic ratios of O/Cr for other chromium compounds are also shown in the figure. The purity of chromium oxides was found to depend on the synthesis pressure and temperature. By increasing the oxygen pres-

* Electrochemical Society Student Member.

** Electrochemical Society Active Member.

z Fax: 803-777-8265




Figure 1. (a) O/Cr ratios (x values) as a function of weight loss observed from TGA. Samples A, B, C, and D were prepared at different temperatures and pressures and $m\text{-CrO}_x$ refers to chemically modified CrO_x . Some chromium oxides are also shown in the graph as reference. A sample TGA curve (sample C) shows how the analysis was done. (b) XRD patterns of $m\text{-CrO}_x$ and $m\text{-LiCrO}_x$. The crystallinity of the $m\text{-CrO}_x$ oxide host lattice suffers severely during chemical lithiation.

sure more pure product was obtained (see sample D and $m\text{-CrO}_x$). As shown in Fig. 1a, the electrode with the highest O/Cr ratio (2.653) has a stoichiometry close to Cr_2O_8 . The diffractograms of $m\text{-CrO}_x$ and $m\text{-LiCrO}_x$ are shown in Fig. 1b. The crystallinity of the $m\text{-CrO}_x$ oxide host lattice suffers severely on chemical lithiation.

The particle size of both lithiated and nonlithiated chromium oxide is in the range of 2–4 μm . The particle size of lithiated CrO_x appears to be slightly smaller than that of CrO_x . Brunauer-Emmett-Teller (BET) surface area determinations (N_2 adsorption) show surface areas of 2 and 3.45 m^2/g for CrO_x and $m\text{-LiCrO}_x$, respectively. The morphology of chromium oxide particles is not clear but it may be described as an aggregation of small particles. Apparently, the size and shape of the particles have not changed considerably by lithiation.

Figure 2 shows the first discharge curves for various chromium oxides prepared at different temperatures and pressures. Sample D and chemically modified chromium oxide $m\text{-CrO}_x$ were prepared at higher pressures compared to samples B and C. The initial capacity of $m\text{-CrO}_x$ is 255 mA/g . The oxides prepared at lower pressures have impurities, which result in a small plateau at the start of discharge. As shown in Fig. 2, the plateau decreases as the pressure increases, and disappears completely in the case of $m\text{-CrO}_x$. Also, the average voltage depends on the synthesis temperature and pressure of the active material. The voltage increases from 2.5 to 3.0 V as the pressure in the autoclave is increased. The reversibility of $m\text{-CrO}_x$ cathode material was tested using cyclic voltammetry. Figure 3 shows a cyclic voltammogram for CrO_x obtained at 0.05 mV/s . The voltage was varied between 2.0 and 4.3 V. As shown in Fig. 3, this cathode material is very reversible over the entire intercalation range with a small capacity loss after the first discharge. The structural change during intercalation was avoided by not allowing Cr(VI) to reduce to Cr(III) ,




Figure 2. First discharge curves of various chromium oxides (CrO_x).




Figure 3. Cyclic voltammograms of $m\text{-CrO}_x$ obtained at a sweep rate of 0.05 mV/s .




Figure 4. Capacity vs. cycle number for various chromium oxides. The initial capacity of other prominent cathode materials is also shown for comparison.

which may result in structural breakdown.¹¹

Figure 4 shows the capacity of $m\text{-CrO}_x$ as a function of cycle number. The capacity after 50 cycles is still 210 mA/g . The initial capacities of commercial cathode materials (LiMn_2O_4 , LiCoO_2 , and LiNiO_2) are also shown in the same graph. Cycling of samples B, C, and D was stopped after the first few cycles because their capacity was lower than the capacity of $m\text{-CrO}_x$. All electrodes were cycled at the discharge rate of 0.1 mA/cm^2 . High capacity and small capacity fade make $m\text{-CrO}_x$ an attractive cathode material in secondary lithium batteries.

Figures 5a and b show cyclic voltammograms of LiCr_2O_8 and $m\text{-LiCrO}_x$, respectively, obtained at a sweep rate of 0.05 mV/s . The voltage was varied between 1.0 and 4.0 V for LiCr_2O_8 and between 2.0 and 4.3 V vs. Li/Li^+ for $m\text{-LiCrO}_x$. As shown in Fig. 5a, two peaks are observed at 1.6 and 3.25 V during intercalation, and two peaks at 2.1 and 3.8 V during deintercalation. The separation between the peaks indicated high irreversibility with a large capacity loss between




Figure 5. Cyclic voltammograms of (a) LiCr_3O_8 and (b) $m\text{-LiCrO}_x$ obtained at sweep rate of 0.05 mV/s.

the first and second cycle. Figure 5b shows that only one peak was obtained during intercalation (at 3.5 V) in $m\text{-LiCrO}_x$ and one peak during deintercalation at 3.2 V vs. Li/Li^+ . The small peak separation indicates that this cathode material is reversible over the entire intercalation range.

Figures 6a and b show the charge-discharge curves obtained for LiCr_3O_8 and $m\text{-LiCrO}_x$. The electrode in Fig. 6a was cycled between 1.0 and 4.0 V vs. Li/Li^+ reference electrode. As shown in this figure, the LiCr_3O_8 structure is not stable and after the first cycle two plateaus appear with a large capacity loss. Similar results were observed by Koksang et al.¹² They found that the Li insertion/deinsertion reaction in LiCr_3O_8 involves irreversible structural changes with the presence of three plateaus at ca 2.9, 2.25, and 1.8 V.

The charge-discharge curves for $m\text{-LiCrO}_x$ shown in Fig. 6b when cycled between 2.0 and 4.2 V at the rate of 0.1 mA/cm² showed an initial capacity of 210 mAh/g. Only one plateau was observed during charge and discharge indicating that the structure is stable and reversible over the entire intercalation range. The results clearly indicate that $m\text{-LiCrO}_x$ has different electrochemical characteristics than LiCr_3O_8 reported in literature. $m\text{-LiCrO}_x$ can be used as a positive electrode with any carbon negative electrode in a lithium-ion cell, while CrO_x can be used with lithium or lithiated carbon as a negative electrode in lithium or lithium-ion secondary cells.

Conclusions

Chemically modified $m\text{-CrO}_x$ was synthesized by heating CrO_3 in an autoclave under high oxygen pressure. The CrO_3 impurity was removed by leaching and by chemically treating the product, thus making CrO_x environmentally friendly. This compound is neither hygroscopic nor soluble in water. Synthesis temperature and pressure markedly affected the performance of CrO_x . Higher pressures resulted in higher O/Cr ratio and less impurities in the final product. The shape of the discharge curves and cyclic voltammograms indicate no structural changes during lithium insertion. The discharge capacity of $m\text{-CrO}_x$ exceeded 250 mAh/g, when cycled between 2.0 and 4.2 V, and the energy density of this electrode is ca. 600-650 Wh/kg. The




Figure 6. Charge-discharge curves of (a) LiCr_3O_8 and (b) $m\text{-LiCrO}_x$. The numbers on figure refer to cycle number.

electrode prepared from $m\text{-CrO}_x$ exhibited negligible capacity fade when cycled between 2.0 and 4.2 V at a current density of 0.1 mA/cm². This material can be used as a positive electrode with lithium or lithiated carbon as a negative electrode in secondary lithium cells.

The chemical lithiation of CrO_x was carried out using active LiI in acetonitrile. Charge and discharge studies indicated that this material is stable and reversible over the entire intercalation range with an initial capacity of 210 mAh/g. $m\text{-LiCrO}_x$ can be used as a positive electrode with a carbon negative electrode in the lithium-ion cell.

Acknowledgments

The authors gratefully acknowledge the financial support provided by the Department of Energy Division of Chemical Sciences, Office of Basic Energy Sciences, under contract no. G.M. DE-FG02-96ER 146598.

The University of South Carolina assisted in meeting the publication costs of this article.

References

1. J. Desilvestro and O. Haas, *J. Electrochem. Soc.*, **137**, 5C (1990).
2. D. Linden, in *Handbook of Batteries and Fuel Cells*, D. Linden, Editor, p. 11, McGraw-Hill, Inc., New York (1984).
3. Y. Toyoguchi, J. Yamamura, T. Matsui, and J. Iijima, Abstract 73, p. 109, The Electrochemical Society Extended Abstracts, Vol. 87-2, Honolulu, HI, Oct 18-23, 1987.
4. Y. Takeda, R. Kanno, Y. Oyabe, and O. Yamamoto, *J. Power Sources*, **14**, 215 (1985).
5. O. Yamamoto, Y. Takeda, R. Kanno, Y. Oyabe, and Y. Shinya, *J. Power Sources*, **20**, 151 (1987).
6. J. O. Bessenhard and M. Schwaker, *J. Power Sources*, **26**, 409 (1989).
7. J. O. Bessenhard and R. Schollhorn, *J. Electrochem. Soc.*, **124**, 968 (1977).
8. J. M. Tarascon and D. Guyomard, *J. Electrochem. Soc.*, **138**, 2864 (1991).
9. P. Arora, B. N. Popov, and R. E. White, *J. Electrochem. Soc.*, **145**, 807 (1998).
10. P. Arora, G. Zheng, B. N. Popov, and R. E. White, Abstract 90, p. 104, The Electrochemical Society Extended Abstracts, Vol. 97-1Montreal, Quebec, Canada, May 4-9, 1997.
11. R. Koksang and P. Norby, *Electrochim. Acta*, **36**, 127 (1991).